

MAIN OFFICE
1455 New York Ave
Huntington, Sta, 11746
(631) 427-5904
FAX (631) 673-3301

PLANT
366 Moffitt Ave
Islip, NY, 11751
(631) 277-0570
FAX (631) 277-0913

VelveTop™

P R O D U C T S

Specifications: Driveway Patch & Crack Filler

GENERAL DESCRIPTION

VelveTop™ Driveway Patch & Crack Filler is a trowelable, sand filled asphalt emulsion of the mineral colloid type which has been fortified with inorganic reinforced fibers. Its mortar like consistency make it useful to fill cracks up to ¾" deep, level low areas, and fill small holes. Since hand applied mastics are subject to greater shrinkage stresses than those which have been densified with power compaction equipment, the reinforced fibers provide greater tensile strength in the uncured mix.

PHYSICAL PROPERITIES

Type	Mineral Colloid Emulsion
Vehicle	Water
Fiber	Inorganic Type
Consistency	Medium Paste
Application Temperature	Avoid freezing during application and while curing. For best results apply and cure at temperatures above 50° F.

GENERAL APPLICATION PROCEDURE

Remove all dirt and loose material from surface; Flush and let dry if necessary. Use steel trowel or wood float to work filler into low area or crack, working from deepest point to feather edge. For easier application, keep tools damp. Allow to dry thoroughly before using area or applying coats of other material.

SAFETY PRECAUTIONS

Harmful if swallowed; keep out of reach of children.

APPLICATION PRECAUTION

Keep from freezing. Keep container covered when not in use. Do not apply in rain or when frost or rain is forecasted before material has cured. As temperature and humidity affects curing time, application on warm, sunny days are recommended. Apply only when air temperature is 50° F and rising.

SHIPPING SIZE AND WEIGHT

1 gallon pail	10 lbs.
3.5 gallon pail	35 lbs.
5 gallon pail	50 lbs.
55 gallon drum	550 lbs.

WARRANTY

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent inferred.

