

The Pro's Choice
Since 1936

PRODUCT #11060, 11150



FAST SETTING ULTRA HIGH STRENGTH CONCRETE MIX

DESCRIPTION

SAKRETE® Fast Setting Concrete Mix is a mixture of sand, coarse aggregate, cement and special additives

FEATURES AND BENEFITS

- 5000 psi (34MPa), exceeds ASTM C 387
- Quality controlled
- Poly-lined moisture resistant bag
- Sets poles and posts without mixing or bracing
- Sets in 1/2 hour: Walk on in 8 hours
- Just add water and mix
- Rapid strength gain allows same day use

APPLICATIONS

- For building or repairing walkways, floors, footings and patios
- Setting poles and posts.
- For applications of 2 inches (50 mm) in thickness or more.

SAFETY

Read and understand the MSDS before using this product. **Keep out of reach of children.**

PREPARATION

When repairing concrete, remove all loose and foreign material. Dampen adjoining concrete surfaces.

MIXING

Empty the contents into a mortar box, wheel barrow, or mechanical mixer. When mixing by hand, form a crater for adding water. See table below. If too stiff, add more water a little at a time. Avoid a soupy mix. Excess water reduces strength and durability and can cause cracking. In cold weather use warm water to accelerate the set. Use cool water to slow the set in hot weather. Do not mix more material than can be used in 15 minutes.

| | |
|-----------------|-----------------------|
| 50lb. (22.6kg) | 2.5-3 qts. (2.3-2.8L) |
| 60 lb. (27.2kg) | 3-3.5 qts. (2.8-3.3L) |

Water amounts are approximate

PLACEMENT

Place and consolidate the SAKRETE® Fast Setting Concrete Mix. Work the material into voids then level the surface with a straight edge board. Allow freshly placed concrete to set until the surface water has begun to disappear before finishing. Time will vary with weather conditions.

FINISHING

Begin finishing when the surface is firm to the touch. Time will be shorter in hot weather and longer in cold weather. For a rough surface use a wood float. After floating use a broom or brush to texture the surface. For a smooth surface use a steel trowel. Use an edging tool.

CURING

In hot weather cover with a wet clean curing cloth and plastic. Keep continuously wet for a minimum of 1 day. In cold weather adequately cover and keep from freezing for a minimum of 24 hours.

DIRECTIONS FOR SETTING POSTS WITHOUT MIXING

1. Dig hole to desired size and place approximately 2 inches gravel (50 mm) in bottom.
2. Fill hole approximately 1/3 full with clean water. (Hot water causes faster set). Damp or wet soil may require less water than dry or sandy soil.
3. Place post in hole as desired. Pour or shovel SAKRETE® Fast Setting Concrete into hole evenly. When dry mix fills hole to water level, add more water and dry mix until hole is full. Be sure post is aligned as required.
4. When hole is full, lightly tamp or trowel top of concrete to consolidate and shape surface. If necessary, a small amount of water may be sprinkled on the surface to aid with finishing.

STORAGE

Store in a tightly closed container off the floor in a dry place.

TECHNICAL DATA

Exceeds ASTM C 387 when used as directed

Compressive Strength

| | |
|--------|--------------------|
| 3 day | 2,470 psi (17 MPa) |
| 7 day | 3,480 psi (24 MPa) |
| 28 day | 5,000 psi (34 MPa) |

PRECAUTIONS

- This product sets much faster than ordinary concrete.
- Do not mix more material than can be used in 15 minutes.
- Do not place when temperatures are below 40°F (4°C)
- Protect from freezing for 24 hours

COVERAGE

| Bag size | Yield |
|------------------|--------------------------|
| 50 lb. (22.6 kg) | .38 cu. ft. (.011 cu. m) |
| 60 lb. (27.2 kg) | .45 cu. ft. (.012 cu. m) |

To determine the number of bags needed:
Multiply (length x width x depth) divided by yield

POST ESTIMATING GUIDE

Number of bags required assuming a 10 inch (.25m) diameter hole

| | 12 in. (.3m) | 18 in. (.45m) | 24 in. (.6m) | 30 in. (.76m) |
|--------|--------------|---------------|--------------|---------------|
| 50 lb. | 1.4 | 2.2 | 2.9 | 3.6 |
| 60 lb. | 1.2 | 1.8 | 2.4 | 3.0 |

(Continued on back)

The Pro's Choice
Since 1936

PRODUCT # 11060, 11150



FAST SETTING ULTRA HIGH STRENGTH CONCRETE MIX

PACKAGING

50 lb. bag (22.6 kg) - UPC: 7-64661-11150-4

60 lb. bag (27.2 kg) - UPC: 7-64661-11060-6

All sizes not available in all areas

WARNING! CAUSES IRRITATION – Avoid contact with eyes, skin and clothing. Wash thoroughly after handling. Exposure may result in irritation of the skin, eyes, or nasal passages from alkali in cement. When wet, contact with the skin or eyes may result in irritation or burns. **FIRST AID:** In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get prompt medical attention; for skin, wash thoroughly with plenty of soap and water. **HARMFUL IF INHALED** – Avoid breathing dust. Keep container closed. Use with adequate ventilation. Excessive exposure by inhalation over an extended period of time may result in the development of pulmonary diseases including pneumoconiosis and silicosis. Crystalline Silica has been classified by IARC and NTP as a carcinogen.

LIMITED PRODUCT WARRANTY

The manufacturer warrants that this product shall be of merchantable quality when used or applied in accordance with the manufacturer's instructions. This product is not warranted as suitable for any purpose other than the general purpose for which it is intended. This warranty runs for one (1) year from the date the product is purchased. ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ON THIS PRODUCT IS LIMITED TO THE DURATION OF THIS WARRANTY. Liability under this warranty is limited to replacement of defective product or, at the manufacturer's option, refund of the purchase price. CONSEQUENTIAL AND INCIDENTAL DAMAGES ARE NOT RECOVERABLE UNDER THIS WARRANTY.

The SAKRETE Companies

866-SAKRETE

866-725-7383

Sakrete® and the background design are registered trademarks of SAKRETE, Inc., Cincinnati, OH 45217 ©2002