

# TETRA FLAKE DRY CALCIUM CHLORIDE

**Product Data Sheet** 

## **General Description**

TETRA Flake calcium chloride is a white, flaked, dihydrate product with 77 weight percent calcium chloride.

# **Applications**

**Chemical Industry.** Provides good source of soluble calcium

**Oilfield.** Can be used as fluid for drilling, cementing, and workover operations

Ready Mix Concrete. Accelerates setting times

**Snow and Ice Melting.** Facilitates deicing on highways and pavement

**Soil Conditioning.** Stabilizes roadbeds and facilitates salt remediation

**Water Care.** Provides source of calcium for pools and nonpotable applications

# **Availability**

FLAKE PACKAGING				
Package	Pallet Size	Units/ Pallet	Pallets/ Truckload	
50 lb Plastic Bag	A variety of palletization and stow options are available.			
1000 kg Bulk Bag				

#### Safety and Handling

TETRA flake calcium chloride when in solution form is a strong salt solution. Protective clothing, rubber gloves and eye protection are recommended. Rubber safety boots should also be worn in work areas, since calcium chloride can damage leather. This product should be handled in areas with proper ventilation. Before using this product, refer to the MSDS (available on the Company's website) for complete safety and handling guidelines. For proper disposal guidelines for calcium chloride wastes, consult the appropriate local regulatory authorities.

CHEMICAL PROPERTIES		
Chemical	CaCl <sub>2</sub>	
Appearance	White flakes	
Assay	77% minimum by weight CaCl <sub>2</sub>	
<b>Bulk Density</b>	Approx. 50 lb/cubic foot	
рН	8.0 to 10.5 (at 5 to 38% wt solutions)	

TYPICAL ANALYSIS*		
Sodium Chloride (NaCl)	< 4.0% by weight	
Potassium Chloride (KCl)	< 1.5% by weight	
Magnesium Chloride (MgCl <sub>2</sub> )	< 0.5% by weight	
Iron (Fe)	< 0.002% by weight	
Heavy Metals	< .005% by weight	
Sulfates (as SO <sub>4</sub> )	< .075% by weight	
Water Insolubles	< .03% by weight	
Alkalinity (as CaCO <sub>3</sub> )	< .20% by weight	
*impurities based on 100% CaCl <sub>2</sub> basis		

TYPICAL SCREEN ANALYSIS		
Screen Number:		
4 (4.76 mm)	80-100% passing by weight	
8 (2.38 mm)	75% passing by weight	
30 (0.59 mm)	5% passing by weight	

### **TETRA Chemicals**

25025 Interstate 45 North, Suite 600 The Woodlands, Texas 77380

Phone: 281.367.1983

Customer Service: 800.327.7817

**Fax:** 281.298.7150

#### www.tetrachemicals.com

Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. Further, nothing contained herein shall be taken as a recommendation to manufacture or use any of the herein described materials or processes in violation of existing or future patents.