

MAIN OFFICE  
1455 New York Ave  
Huntington, Sta, 11746  
(631) 427-5904  
FAX (631) 673-3301

PLANT  
366 Moffitt Ave  
Islip, NY, 11751  
(631) 277-0570  
FAX (631) 277-0913

# VelveTop™

## P R O D U C T S

### Specifications: VelvaFlex Pourable Crack Filler

#### GENERAL DESCRIPTION

VelvaFlex Pourable Crack Filler is a rubberized asphalt emulsion with greater flexibility designed for filling narrow pavement cracks up to ½” in width, in asphaltic as well as concrete surfaces. It has resilient characteristics that can allow self threading quality or memory. It has excellent flow properties and no pin holing. It is ready to used on parking lots, airports, athletic courts, driveways, traffic safety islands, playgrounds, and walkways. VelvaFlex meets Emulsified Asphalt’s AASHTD designation M140-70, ASTM designation D977-73 and D-244 testing emulsified asphalts.

#### GENERAL APPLICATION PROCEDURE

VelvaFlex is ready to use as is. It can be applied by the pour pot method, crack filling machines or in the quart or gallon sizes, straight from the container. Pour VelvaFlex into cracks. Scrape excess from surface using rubber V squeegee. Allow to cure completely before applying coats of other material.

#### COVERAGE RATE

Approximately 80 linear feet ½” x ½” cracks per gallon.

#### SAFETY PRECAUTIONS

Harmful if swallowed; keep out of reach of children.

#### APPLICATION PRECAUTION

Keep from freezing. Keep container covered when not in used. Do not apply in rain or when frost or rain is forecasted before material has cured. As temperature and humidity affects curing time, application on warm, sunny days are recommended. Apply only when air temperature is 50° F and rising.

#### SHIPPING SIZE AND WEIGHT

1 quart	3 lbs.
1 gallon	10 lbs.
5 gallon	50 lbs.

#### WARRANTY

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent inferred.

